


SURGICRYL[®]

MONOFAST

POLYGLYCAPRONE 25



Type	Monofilament
Composition	Polyglycaprone 25, a copolymer made of 75% glycolide and 25% ϵ -caprolactone
Coating	None
Colour	Violet / Beige - undyed
Tissue reaction	Minimal
Absorption	The hydrolytic action by which the material is broken down results in total absorption in approximately 90 to 120 days. Approximately 60% of tensile strength remain after 7 days.
Presentation	Box with 12 sutures



*For quality
&
safety*

The logo for smi, consisting of the lowercase letters "smi" in a bold, blue, sans-serif font with a white outline.

www.sutures.be

SURGICRYL[®]

MONOFAST

POLYGLECAPRONE 25

CHARACTERISTICS

- High tensile strength
- Synthetic
- Breaks down by hydrolysis
- Monofilament with microscopic uniform diameter

- Pliability and softness
- Hermetically sealed packing

BENEFITS

- Excellent tissue support
- Minimal tissue reaction
- Predictable absorption rate
- Soft passage through the tissues without sawing, tissue drag and trauma
- Absence of capillarity (no support of bacterial growth)
- Excellent knot tie down

- Good handling properties
- Easy and secure knotting

- Guaranteed seal and product sterility


INDICATIONS Superficial soft tissue and/or ligation
 especially in General surgery
 Skin closure
 Plastic surgery
 Gastrointestinal surgery
 Gynaecology
 Urology

CONTRAINDICATIONS Cardiovascular surgery
 Neurosurgery
 Ophthalmic surgery

Being absorbable not to use when an extended wound support is required.

Caution in patients with delayed wound healing (e.g. compromised immune system).

TENSILE STRENGTH



ABSORPTION

